

NORBOND®

Z500 Series

Providing durable, long-lasting security

OEM Automotive Grade, Bonding Tape

Saint-Gobain NORBOND® Z500 series bonding tapes are made with durable black, closed-cell polyurethane foam carrying a high performance, acrylic adhesive system. The polyurethane foam carrier is specifically formulated to meet the most demanding exterior applications. Its energy-dissipating properties absorb vibrations, and distribute stress over the entire bond line. The high performance adhesive system is designed especially for today's high solid and clear-coat paint finishes. NORBOND® Z500 is resistant to oxidation, fungi and weathering, providing long performance life.

The Z500 series is specially designed to provide the following features:

- Stress distribution reduces pressure points, thereby minimizing distortion
- High-performance, durable acrylic adhesive provides a strong, long-lasting bond
- Conformable, closed-cell polyurethane foam facilitates die-cutting
- Prevents corrosion of dissimilar materials by eliminating the contact between them
- Standard polyethylene liner excels in automated production

Available Sizes


Standard thickness: .020, .030, .045, .062, .090 and .120 in. (.5, .8, 1.1, 1.6, 2.3, and 3.0 mm)

Master roll size: 56 in. (1422 mm) width. Slit rolls also available.

Standard roll length varies with thickness.

Applications

- Rear deck spoilers
- Bumper trim and inserts
- Wheel well and door edge moldings
- Rocker panels
- Various ornamentation
- Body cladding
- Ground effects
- Air dams
- Pillar trim
- Reveal moldings




SAINT-GOBAIN

NORBOND® Z500 Series – Properties

(Formerly known as Normount)

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

OEM	Specification
Chrysler	MS-CH59 (TYPE B), MS-1294
Ford	WSB-M3G89D, WSS-M11P65
GM	GMW15201 (TYPE II)

* Has been tested and shown to pass requirements of F.M.U.S.S. 302

NORBOND® Z500 – Standard Roll Sizes.

Product No.	Thickness in. (mm)	Typical Value
Z520	.020 (.5)	200 (61)
Z530	.030 (.8)	200 (61)
Z545	.045 (1.1)	200 (61)
Z562	.062 (1.6)	200 (61)
Z590	.090 (2.3)	150 (48)
Z5120	.120 (3.0)	150 (48)

3" I.D. cardboard cores standard

Options (subject to minimum order requirements)

Liner: Powder-blue silicone release coated polyethylene liner is standard. Other liners, such as silicone coated polyester, may be available upon request with minimum order requirement.

Important Instructions

- Paint systems vary greatly, therefore, use should test NORBOND® E500 series bonding tapes on the surface where they will be used. Saint-Gobain recommends testing all products under actual application conditions prior to commercial use.
- Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface.
- Apply a uniform pressure of 15 psi (103 kPa) to promote good contact between the material to be bonded and the tape. The application temperature should be between 60°F and 125°F (16°C to 52°C). It is not recommended to apply these tapes at temperatures below 60°F (16°C), as the adhesive does not flow in this condition and can result in poor bonding.
- Recommended service temperature is between -30°F to 200°F (-34°C to 93°C).
- The adhesion between the substrate and the tape increases with time, typically reaching final bond strength in 72 hours. Heating the product above 105°F (40°C) will accelerate the adhesion process.

Shelf Life



Need more adhesion? Stick with Saint-Gobain NORBOND® Adhesion Promoters.

NORBOND® adhesion promoters are designed to work in conjunction with acrylic, pressure-sensitive adhesive systems (such as those used on NORBOND tapes).

NORBOND® improves bonding on substrates that resist adhesion. It can be used to develop an immediate quick-stick and generally improves pressure-sensitive acrylic adhesive systems. This enhances adhesion to irregular and curved surfaces. Various formulations are available for specific substrates.

NORBOND® is a trademark of Saint-Gobain Performance



Saint-Gobain Performance Plastics

One Sealants Park
Granville, NY 12832

1-800-724-0883
Tel: (518) 642-2200
Fax: (518) 642-2793

foams@saint-gobain.com
www.foams.saint-gobain.com

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.