

## 1020MB SERIES

### Seal against air drafts, light, dust and noise

**Norseal**® 1020 is manufactured by **Saint-Gobain**® Performance Plastics Corporation, Tape Solutions business, and comes with an extremely soft, low density, open cell PVC foam. The open cell nature of this foam allows it to be compressed easily, and to return very quickly to its original height. With a permanent polyester liner, it is ideal for open and close applications.

**Norseal** 1020 is not intended for use as a water seal, because of the open cell structure, but it is still an excellent seal against air drafts, light, dust, or even noise, when compressed 15%.

The acrylic adhesive used on the **Norseal** product line is a pressure sensitive adhesive and therefore must be applied to clean, dry surfaces. Note: The adhesion performance decreases with time; we therefore recommend use within 6 months after delivery.

If there are any questions regarding this product, please feel free to contact your Customer Care representative.



### APPLICATIONS

- Partition walls
- Doors & windows
- Light suspended ceilings
- Anti-squeak
- Environmentally controlled rooms
- Corrugated walls

**Norseal 1020MB Series - Properties**

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Value	Test Method
Density (kg/m <sup>3</sup> )	100 - 160	ASTM D-1667
Compression, 50% (N/cm <sup>2</sup> )	0.7 - 2.5	ASTM D-1667
Deflection, 50% (N/cm <sup>2</sup> )	0.2 - 0.8	ASTM D-1667
Hardness (shore 00)	10	ASTM D-2240
Tensile (N/cm <sup>2</sup> )	17	DIM 53571
Elongation (%)	190	DIM 53571
Service Temperature (°C)	-30 to +70	

**Storage**

Material should be stored at 21°C, 50% relative humidity.

**IMPORTANT:** It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to your actions or inactions, including your use, design, fabrication or application of the products into which the materials are incorporated.

**WARRANTY:** This document should not be considered a warranty or a guarantee. The descriptions of the Product provided hereinabove may vary based on specifications requested and testing protocols. Typically, Saint-Gobain warrants that product(s) will meet mutually agreed specifications at delivery and Saint-Gobain honors any breach of warranty claims for six (6) months from delivery of the products. If a product is determined to be nonconforming with its warranty, Saint-Gobain's sole obligation is, at its option, to either replace the nonconforming products or reimburse the purchase price for the same.

The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. **SAINT-GOBAIN DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR USE.**

Form #1339 | © Saint-Gobain April 2025 | All the mentioned trademarks are registered trademarks of Saint-Gobain Tape Solutions or affiliates, part of Saint-Gobain group.



**TAPE SOLUTIONS**

North America | South America  
Europe | Asia

For more information, please visit  
[tapesolutions.saint-gobain.com](http://tapesolutions.saint-gobain.com)