



FOAM EXTRUSIONS

Norseal® Foam Extrusions with or without pressure-sensitive adhesive

PVC foam extrusion & thermoplastic elastomers. Features a «skin» which substantially eliminates open surface cells.

Designed for special applications

Norseal Foam Extrusions are manufactured by **Saint-Gobain®** Performance Plastics Corporation, Tape Solutions business, and intend to provide a faster and more economical solution to special sealing applications, including appliance seals, automotive seals, and sealants for metal building and prefabricated construction applications. Foam extrusions are available with or without adhesive and in a variety of densities to meet the needs of different applications.

Norseal Foam Extrusion characteristics

Foam extrusions have a number of features specifically intended to enhance user productivity. The extrusions feature a «skin» which substantially eliminates open surface cells. The cell structure also requires less material to achieve a positive seal. Foam extrusions are resistant to weather, oxidation and fungi and remain flexible at low temperatures.

Features & Benefits

- Long spooled lengths are ideal for long production runs.
- Provide excellent seal against light, dust and moisture.
- Cell structure of foam requires less material to achieve a positive seal.
- Resistant to weather, oxidation and fungi.
- Pressure-sensitive adhesive available for increased versatility.



APPLICATIONS

- Appliance seals
- Metal building and prefabricated constructions
- Transportation
- Commercial refrigeration
- Automotive sealants



Norseal Foam Extrusions – Properties

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

P3150 (PVC, without adhesive)

Profile	Size mm	Length m	Colour	Density kg/m ³	Hardness Shore OO	Tensile Str. N/cm ²	Elongation %	FTC N/100mm	CFD N/100mm	C Set %	Watertight U-Test (100mmH)
●	4.8	1230	Black	150	60-70	80-90	90-100	15	5	< 10	Pass
●	6.1	700	Black	150	60-70	90-110	120-150	15	5	< 10	Pass
●	7.6	500	Black	170	60-70	90-110	120-150	20	7	< 10	Pass
●	8.0	450	Black	170	60-70	90-110	120-150	20	7	< 10	Pass
●	9.0	320	Black	180	60-70	90-110	120-150	25	8	< 10	Pass
●	10.0	300	Black	200	60-70	90-110	120-150	30	10	< 10	Pass
●	12.4	190	Black	220	60-70	90-110	120-150	25	8	< 10	Pass

P4000 Series (Thermoplastic Elastomer, with or without adhesive)

	Profile	Adhesive	Colour	Size mm	Density kg/m ³	Compression set*	Force to compress**	Deflection***	Tensile strength N (kPa)	Elongation %	Water absorption % mass (%volume)	Water sealability****
P4002	●	No	Black	5	150	4 / 1	11 (12)	39 (39)	8 (438)	128	3 (1)	Over 24hrs
P4003	●	No	Black	5	120	4 / 2	5 (5)	15 (15)	6 (311)	89	7 (2)	Over 24hrs
P4021A	●	No	Black	6.5	120	4 / 2	5	14	11 (320)	70	6 (1)	Over 24hrs
P4021G	●	No	Grey	7	120	- / 2	5	14	14 (425)	123	9 (2)	Over 24hrs
P4022	●	No	Black	9	130	4 / 2	7 (8)	18 (18)	18 (322)	98	8 (1)	Over 24hrs
P4102	■	No	Black	3 × 8	150	6 / 3	10 (10)	44 (47)	9 (301)	109	4 (1)	Over 24hrs
P4103	■	5mm	Grey	3.5 × 8	120	3 / 1	9 (11)	47 (52)	9 (266)	27	4 (1)	Over 24hrs
P4163	■	8mm	Black	7 × 14	130	3 / 1	16 (19)	66 (67)	29 (325)	78	4 (1)	Over 24hrs
P4207	▲	Yes	Black	4.1 × 5.2	250	3 / 1	5.1	38.7	10.7 (879)	117	7	Over 24hrs
P4312	◐	8mm	Black	6 × 10.5	160	4 / 1	13 (16)	78 (78)	23	56	3 (-)	Over 24hrs
P4315	■	8mm	Grey	12 × 14	130	3 / 2	21 (26)	110 (116)	68 (383)	140	2 (1)	Over 24hrs

* 30min/24 hrs - 25% compression at RT
 ** N/100mm (result at -10°C) - 30% compression
 *** N/100mm (result at -10°C) - 70% compression
 **** Water depth : 30mm - 30% compression

Items are subject to Minimum Order Quantities. Please contact our Sales Representative for details.

IMPORTANT: It is the user’s responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to your actions or inactions, including your use, design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: This document should not be considered a warranty or a guarantee. The descriptions of the Product provided hereinabove may vary based on specifications requested and testing protocols. Typically, Saint-Gobain warrants that product(s) will meet mutually agreed specifications at delivery and Saint-Gobain honors any breach of warranty claims for six (6) months from delivery of the products. If a product is determined to be nonconforming with its warranty, Saint-Gobain’s sole obligation is, at its option, to either replace the nonconforming products or reimburse the purchase price for the same.

The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR USE.



TAPE SOLUTIONS

North America | South America
 Europe | Asia

For more information, please visit
tapesolutions.saint-gobain.com