

## SILICONE COATED FABRICS

# SCF1032

**SCF1032** is manufactured by **Saint-Gobain**<sup>®</sup> Performance Plastics Corporation, Tape Solutions business, and comes with a silicone rubber-coated fiberglass **Norgard**<sup>®</sup> Fabric, featuring abrasion resistance, excellent electrical properties and an operating temperature range of -85°F to +500°F.

*\*Previously known as **CHEMFAB**<sup>®</sup> SCF1032*



### FEATURES AND BENEFITS

- Chemically inert
- Non-stick and washable
- Thermally stable from -85 to +500°F
- Non-flammable/fire resistant
- Excellent heat transfer
- Dimensionally stable
- High dielectric strength
- Low electrical losses

### AVAILABILITY

- Available in widths up to 36 inches
- Color: White

\*Pictures shown are for illustration purpose only.



### APPLICATIONS

Common applications include:

- Electrical gasketing
- Heater covering
- Conveyor belts
- Shrink tunnel curtains

## TYPICAL PROPERTIES

Property	Value	Unit
Widths Available	36	inches
Weight	32.0	oz/yd <sup>2</sup>
Thickness	0.0320	inches
Fiberglass Thickness	0.0150	inches
Breaking Strength (Warp)	400	lbs/in
Breaking Strength (Fill)	300	lbs/in
Trapezoidal Tear (Warp)	12,000	gr
Trapezoidal Tear (Fill)	12,000	gr
Thread Count (Warp)	28	-
Thread Count (Fill)	16	-
Elongation at 40 lbs/in	<10	%
Temperature Resistance	-85 to +500	°F
Burst, Diaphragm	200	psi

The values presented are typical values and should not be used for specification purposes. Contact your **Saint-Gobain** Tape Solutions representative for more information.



### TAPE SOLUTIONS

North America | South America  
Europe | Asia

For more information, please visit  
[tapesolutions.saint-gobain.com](https://tapesolutions.saint-gobain.com)

**IMPORTANT:** It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to your actions or inactions, including your use, design, fabrication or application of the products into which the materials are incorporated.

**WARRANTY:** This document should not be considered a warranty or a guarantee. The descriptions of the Product provided hereinabove may vary based on specifications requested and testing protocols. Typically, Saint-Gobain warrants that product(s) will meet mutually agreed specifications at delivery and Saint-Gobain honors any breach of warranty claims for six (6) months from delivery of the products. If a product is determined to be nonconforming with its warranty, Saint-Gobain's sole obligation is, at its option, to either replace the nonconforming products or reimburse the purchase price for the same.

The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR USE.