

9200 SERIES

High-Performance Solid Silicone Rubber

Saint-Gobain® Norseal® 9200 Series Solid Silicone Rubber in square sheet and continuous length form is manufactured by **Saint-Gobain** Performance Plastics Corporation, Tape Solutions business, and features a medium smooth, blemish-free surface. It is available in degrees of hardness ranging from relatively soft 30 and 50 durometer on the Shore A scale. It is manufactured in different formulations to provide a choice of physical properties and cost considerations. **Norseal** 9200 Series provides excellent tensile strength and superior tear resistance. It is tougher and more resilient than general purpose silicone and withstands temperatures ranging from -100°F to +400°F.

Norseal Solid Silicone products are specially intended to provide the following features:

- Superior tear and cut through resistance
- Smooth, defect-free surface
- Low compression set
- Low outgassing
- Excellent release characteristics
- Long service life
- Good chemical and fluid resistance
- Capable of meeting ZZ-R-765, class 3B, A-A-59588, 3B

Available Sizes

Standard thickness: .031, .063, .094 and .125 in.

Master roll size: 36 in. (914 mm) × continuous length

Special thickness and roll sizes also available.



APPLICATIONS

- Lamination/bonding particle boards
- Helicopter blades
- Office equipment
- Missiles
- Walk-in bathtubs
- Boat hauling
- Military equipment

Norseal 9200 Series — Properties

(COHRLastic® 9200)

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Test Method	9235	9255
Durometer: Shore A	ASTM D2240	30	50
Tensile Strength: psi	ASTM D412	1150	1200
Tear Strength	ASTM D624	150	160
Elongation: %	ASTM D412	800	600
Compression Set: % %, 70 hours @302°F	ASTM 395	30	30
Dielectric Strength: volts/mil	-	500	500
Thermal Conductivity: BTU, in./hr. ft.2 °F	-	1.2	1.3
Temperature Range: °F	-	-100 - +400	-100 - +400
Color	Visual	Gray	Gray

Norseal 9200 — Standard Roll Sizes

Product No.	Thickness in. (mm)
9235	.031, .063, .094, .125 (.79, 1.59, 2.38, 3.18)
9255	.031, .063, .094, .125 (.79, 1.59, 2.38, 3.18)

Roll width: 36 in. × continuous length

Options (subject to minimum order requirements)

Powder-free interleaf liner added for ease in winding.

Acrylic (or silicone) pressure-sensitive adhesive (PSA) available in sheet format only (see **Norseal** Silicone Elastomer Adhesive Option data page for details).

Important Instructions

Because **Saint-Gobain** cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.

Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface. Do not remove liner until tape is in proper position. Avoid touching adhesive surface before application.

Recommended service temperature of the silicone elastomer is -100°F to 400°F (-73°C to 204°C).

Shelf Life

120 months from date of shipment for base material when stored in original packaging at temperatures up to 70°F (21°C), < 50% relative humidity, and away from direct sources of heat and direct sunlight. (See the applicable data sheets for pressure sensitive adhesive options).

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to your actions or inactions, including your use, design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: This document should not be considered a warranty or a guarantee. The descriptions of the Product provided hereinabove may vary based on specifications requested and testing protocols. Typically, Saint-Gobain warrants that product(s) will meet mutually agreed specifications at delivery and Saint-Gobain honors any breach of warranty claims for six (6) months from delivery of the products. If a product is determined to be nonconforming with its warranty, Saint-Gobain's sole obligation is, at its option, to either replace the nonconforming products or reimburse the purchase price for the same.

The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR USE.

Form #1049 | © Saint-Gobain March 2026 | All the mentioned trademarks are registered trademarks of Saint-Gobain Tape Solutions or affiliates, part of Saint-Gobain group.



TAPE SOLUTIONS

North America | South America
Europe | Asia

For more information, please visit
tapesolutions.saint-gobain.com