


## EXTRUDED PTFE FILMS

# R128 & R129

**R128** and **R129** Extruded PTFE Films are engineered for use as the primary insulation in high temperature wire and cable and wall construction of convoluted hoses. **Norgard™** R128 and R129 are designed for the most demanding applications requiring high performance and tight tolerances while providing excellent dielectric strength, thermal and chemical resistance.

*\*Previously known as*

**FLUOROWRAP® A EXTRUDED PTFE FILM**



### FEATURES AND BENEFITS

- High dielectric strength
- Outstanding thermal and chemical resistance
- Meets MIL-W-16878/4A, 7139B, MIL-W-22759B and NAS703

### AVAILABILITY

- **Norgard R128:** Available in white and natural
- **Norgard R129:** Available in a wide range of colors
- Available on industry standard 3" (76 mm) ID cores in-flat pad, traverse wound or StablEdge™ packages
- Slit widths are available at 0.10" (2.5 mm) or wider
- Customized solutions available

### APPLICATIONS

- Wire and cable insulation for extreme chemical and thermal environments
- Power cable
- Coaxial cable
- Thermocouple wire
- Convoluted hose constructions

\*Pictures shown are for illustration purpose only.



## TYPICAL PROPERTIES

Thickness	2.0 mil	3.0 mil	4.0 mil	5.0 mil	10.0 mil	Unit
Thickness (metric)	0.051	0.076	0.102	0.127	0.254	mm
Density	1.6	1.6	1.6	1.6	1.6	g/cm <sup>3</sup>
Tensile Strength MD (minimum)	2,500	2,300	2,200	1,900	1,000	psi
	17.2	15.8	15.2	13.16.9	38	MPa
Tensile Strength TD (minimum)	250	275	350	350	375	psi
	1.7	1.9	2.4	2.4	2.6	MPa
Elongation (minimum)	75	125	125	150	300	%
Dielectric Strength	6,000	8,000	9,000	11,000	15,000	total Volts
Approximate Yield	60.2	40.1	30.1	24.1	12.0	ft <sup>2</sup> /lb
	12.3	8.2	6.2	4.9	2.5	m <sup>2</sup> /kg

The values presented are typical values and should not be used for specification purposes. Contact your **Saint-Gobain®** Tape Solutions representative for more information.

**IMPORTANT:** It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

**WARRANTY:** For a period of 6 months, Saint-Gobain warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1928 | © Saint-Gobain March 2024 | All the mentioned trademarks are registered trademarks of Saint-Gobain Tape Solutions or affiliates, part of Saint-Gobain group.

