



NORBOND®

V2800 Series

Providing durable, long-lasting security

Black, Closed-Cell, Polyurethane Foam Tape

Saint-Gobain NORBOND® V2800 series bonding tapes combine a black polyurethane foam substrate with a high-performance, pressure-sensitive acrylic adhesive on both sides. The foam substrate allows energy and stress in the joint to be dissipated over the entire bond. NORBOND 2800 is an ideal choice for severe exterior bonding applications. The product is durable in all weather conditions and provides resistance against UV light, extreme temperatures, fungi, oxidation and ozone.

The V2800 series is specially designed to provide the following features:

- Stress distribution reduces pressure points, thereby minimizing distortion
- High-performance, durable acrylic adhesive provides a strong, long-lasting bond
- Conformable, closed-cell polyurethane foam has excellent environmental resistance
- Prevents corrosion of dissimilar materials by eliminating the contact between them
- Standard polyethylene liner excels in automated production

Available Sizes

Standard thickness: .030, .045, .062, .090 and .120 in.

Master roll size: 56 in. (1422 mm) width. Slit rolls also available.

Standard roll length varies with thickness.

Nonstandard roll length available on special order.

Applications

- Window muntin bars
- Emblems and ornamentation
- Trailer roof bows
- Panel stiffeners
- Signs and nameplates
- Weatherstripping
- Body side molding
- Composite panels



NORBOND® V2800 Series – Properties

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Test Method	Value or Rating
Density: lbs/ft ³ (kg/m ³)	ASTM D-1667	30 (480)
Peel Adhesion oz/in (N/m) 180° Peel 15-min. dwell	PSTC-3	108 (1,181)
Dynamic Shear Adhesion: psi (kPa), 72 hr. dwell stainless steel to paint	NTP-5	120 (827)
Dynamic Tensile Adhesion: psi (kPa) 24 hr. dwell aluminum to paint	NTP-11	100 (689)
Tensile Strength of Foam: psi (kPa)	ASTM D-412 DIE C	130 (896)
Elongation of Foam: %	ASTM D-412 DIE C	275
Water Absorption: % by weight	NTP-36	5

NTP: Internal Test Procedure

Options (subject to minimum order requirements)

Liner: Powder-blue polyethylene liner is standard. Other liners may be available with minimum order requirement.

Important Instructions

- Because Saint-Gobain cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.
- Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface.
- Apply a uniform pressure of 15 psi (103 kPa) to promote good contact between the material to be bonded and the tape. The application temperature should be between 60°F and 125°F (16°C to 52°C). It is not recommended to apply these tapes at temperatures below 60°F (16°C), as the adhesive does not flow in this condition and can result in poor bonding.
- Recommended service temperature is between -40°F to 200°F (-40°C to 93°C).
- The adhesion between the substrate and the tape increases with time, typically reaching final bond strength in 72 hours. Heating the product above 105°F (40°C) will accelerate the adhesion process.

Shelf Life

12 months after the date of sale when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity.



Need more adhesion? Stick with Saint-Gobain NORBOND Adhesion Promoters.

NORBOND adhesion promoters are designed to work in conjunction with acrylic, pressure-sensitive adhesive systems (such as those used on NORBOND tapes). NORBOND improves bonding on substrates that resist adhesion. It can be used to develop an immediate quick-stick and generally improves pressure-sensitive acrylic adhesive systems. This enhances adhesion to irregular and curved surfaces. Various formulations are available for specific substrates.

NORBOND® is a registered trademark of Saint-Gobain Performance Plastics.



Saint-Gobain Performance Plastics

One Sealants Park
Granville, NY 12832
1-800-724-0883
Tel: (518) 642-2200
Fax: (518) 642-2793

foams@saint-gobain.com
www.foams.saint-gobain.com

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

NORBOND® V2800 – Standard Roll Sizes

Product No.	Thickness in. (mm)	Length ft. (m)
V2830	.030 (.8)	200 (61)
V2845	.45 (1.2)	200 (61)
V2862	.062 (1.5)	200 (61)
V2890	.090 (2.3)	150 (45)
V28120	.120 (3.0)	50 (15)

3 in. I.D. cardboard cores standard